DEEP CYCLE PROFESSIONAL

6V EU DC-240 Ah (C_{20})



PHYSICAL CHARACTERISTICS		
	SI Units	US Units
Length	244 mm	9,61 inch
Width	190 mm	7,48 inch
Height	274 mm	10,79 inch
Typical weight	29,40 kg	64,82 lbs

Specifications:

- Nominal voltage: 6 V
- Rated capacity: 240 Ah (at C_{20} and 25 °C)
- Plate technology: Antimony / Antimony
- Separator: Polyethylene + glass mat
- Electrolyte: Sulphuric acid (SG 1,28) OCV 6.35V
- Standards: IEC 60254; IEC 61427
- Case / Lid material: Polypropylene
- Lid type: Flat
- Terminal type: Conical
- Carrying Handles: Available
- Cycles at 50% DoD: up to 900 cycles
- PVES applications: up to 2000 cycles

Performance characteristics:


BATTERY DISCHARGE PERFORMANCE AT 25°C				
Discharge rate	**C_5 (5 h)**	**C_{20} (20 h)**	**C_{100} (100 h)**	**Capacity at 25 A**
End of discharge voltage	5,10 V	5,25 V	5,40 V	5,25 V
Discharge capacity	198 Ah	240 Ah	265 Ah	505 min

Temperature correction factor of discharge C_5 (5 h) capacity							
Temperature	-10 °C	0 °C	20 °C	25 °C	30 °C	35 °C	40 °C
Correction factor	0.80	0.88	0.98	1.00	1.03	1.05	1.07


BATTERY CHARGE CONDITIONS AT 25oC

Charging profile: **Charge factor: 1.10 – 1.20**

IUIa –characteristics for flooded batteries



Charging times with IUIa-characteristics in hours at 25 °C




Stage1: Constant current **Stage 2**: Constant voltage **Stage 3**: Constant current


It is mandatory to check the electrolyte level every 3 months and top up with deionized water to the markings.

MONBAT Plc, 32A, Cherni vrah Blvd., fl. 4, 1407 Sofia, Bulgaria, tel: +359 2 962 11 50, fax:+359 2 962 11 46, e-mail: monbat.trading@monbat.com

BATTERY DISCHARGE CURVES AT 25oC

DISCHARGE PERFORMANCE AT CONSTANT CURRENT DISCHARGE (A)





It is mandatory to check the electrolyte level every 3 months and top up with deionized water to the markings.

MONBAT Plc, 32A, Cherni vrah Blvd., fl. 4, 1407 Sofia, Bulgaria, tel: +359 2 962 11 50, fax:+359 2 962 11 46, e-mail: monbat.trading@monbat.com